

Application: An industry favorite, Goodyear's Eclipse profile is very popular for use in general purpose incline applications. The durable all polyester interwoven carcass provides low stretch, excellent fastener retention and good tear resistance. The economical PVG cover compound has superior mineral oil resistance as well as excellent wear characteristics.

Technical Data

	Imperial	Metric
Working Tension	200 PIW	35 KN/M
Number Of Plies	1	1
Fabric Type	thin gauge 200	thin gauge 200
Top Surface	Eclipse	Eclipse
Bottom Surface	Brushed	Brushed
Overall Gauge (Approximate)	0.267 in.	6.78447 mm
Weight (Approximate)	1.23 lbs/sq.ft.	6.0 kg/sq.m.
Bottom Coefficient Of Friction	0.25 (approx.)	0.25 (approx.)
Minimum Rec. Pulley Diameters	3.0 in.	7.62 mm
Elongation At Rated Tension	< 2%	< 2%
Working Temperature	20 to 180 F	-7 to 82 C

Splicing Methods

FOF	Finger	Bias Stepped	Skived Bias	Clipper *	Alligator *	Staple *
No	Yes	No	Yes	4 or U4	27	187

* Fastener manufacturer should be consulted to review belt and application information.

Compliance (Government Regulations)

FDA/USDA	OSHA	MSHA	CSA	FRAS	NCB
	<300 Megohms	CFR 18.65	M422-87	1334.12	158:1989
No	No	No	No	No	No

No warranty, including implied warranty of merchantability, fitness for a particular purpose, or other warranty of quality is either expressed or implied of this product. The information on this specification sheet supercedes all previously printed material.